

10/16/00
j0836 U.S. PTO

UTILITY
PATENT APPLICATION
TRANSMITTAL

for new nonprovisional applications under 37 CFR 1.53(b))

10-17-00

Attorney Docket No.	09792909-4653
First Named Inventor or Application Identifier	
Yoshimasa Saito	
Express Mail Label No: EL65478333US	

j0602 U.S. PTO
09/688733
10/16/00

ADDRESS TO: Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

APPLICATION ELEMENTS <i>See MPEP chapter 600 concerning utility patent application contents.</i>	ACCOMPANYING APPLICATION PARTS
1. <input checked="" type="checkbox"/> Specification Total Pages <u>26</u>	5. <input checked="" type="checkbox"/> Assignment Papers (cover sheet & documentation) <u>Sony Corporation</u>
2. <input checked="" type="checkbox"/> Drawing(s) (35USC 113) Total Pages <u>7</u>	6. <input type="checkbox"/> Letter under 37 CFR 1.41(c).
3. <input checked="" type="checkbox"/> Declaration and Power of Attorney Total Pages <u>2</u>	7. <input type="checkbox"/> English Translation Document (if applicable)
a. <input type="checkbox"/> Unexecuted(original or copy)	8. <input type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input type="checkbox"/> Copies of IDS Citations
b. <input type="checkbox"/> Copy from prior application (37CFR 1.63(d)) (for continuation/divisional with Box 14 completed)	9. <input type="checkbox"/> Preliminary Amendment
[Note Box 4 Below]	10. <input checked="" type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized)
i. <input type="checkbox"/> DELETION OF INVENTOR(S) Signed statement attached deleting Inventor(s) named in the prior application, see 37 CFR 1.63(d)(2) and 1.33(b).	11. <input type="checkbox"/> Small Entity <input type="checkbox"/> Statement filed in prior Application, Status still proper and desired
4. <input type="checkbox"/> Incorporation By Reference (usable if Box 3b is checked) The entire disclosure of the prior application, from which copy of the oath or declaration is supplied under Box 3b, is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein.	12. <input type="checkbox"/>

14. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) ☐ of prior application No:

CLAIMS AS FILED					
	(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA	(4) RATE	(5) BASIC FEE \$710.00
	TOTAL CLAIMS 20	14		0.00	0.00
	INDEPENDENT CLAIMS 03	5		240.00	240.00
		ANY MULTIPLE DEPENDENT CLAIMS? <input type="checkbox"/> YES <input checked="" type="checkbox"/> NO			950.00
				TOTAL FEE	\$950.00

☒ The Commissioner is hereby authorized to charge any additional fees which may be required in connection with this application, or credit any overpayment to ACCOUNT NO. 19-3140. A duplicate copy of this sheet is enclosed.

☒ A check in the amount of \$950.00 to cover the filing fee is enclosed.

15. CORRESPONDENCE ADDRESS: David R. Metzger
SONNENSCHN NATH & ROSENTHAL
P.O. Box #061080
Wacker Drive Station, Sears Tower
Chicago, IL 60606-1080
Customer ID #26263
Telephone (312) 876-8000 - Fax (312) 876-7934

SIGNATURE David R. Metzger
David R. Metzger (Reg. No. 32,919)

DATE October 16, 2000

EXPRESS MAIL #EL654783333US

CERTIFICATE OF MAILING BY "EXPRESS MAIL"

"Express Mail" Mailing Label Number: EL654783333US

Date of Deposit: October 16, 2000

I hereby certify that this correspondence is being deposited with the United States Postal "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to The Commissioner of Patents and Trademarks, Washington, D.C. 20231.

Applicant(s): Yoshimasa Saito

Attorney Docket No. 09792909-4653

\$950.00 Filing Fee (14 claims-6 independent)

Drawings (7 sheets - Figs. 1-7)

Executed Declaration

Executed Assignment, PTO Form 1595 and \$40 recording fee

Return postcard



Signature of Person Mailing Application and Fees

09792909-4653

**LIQUID CRYSTAL DISPLAY ELEMENT
AND
METHOD FOR MANUFACTURING IT**

5 BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display element superior in its viewing angle characteristic. Moreover, the present invention relates to a method including a process of performing a liquid crystal alignment treatment and a pre-tilt angle forming treatment by irradiating a polarized ultraviolet ray for manufacturing a liquid crystal display element superior in its viewing angle characteristic.

15 2. Description of the Related Art

In a mechanical rubbing method that is performed as a liquid crystal alignment treatment at the time of manufacturing a liquid crystal display element, there have been caused problems such as pollution by dust risen at the time of rubbing, electrostatic damage caused by friction to a transparent substrate on which a TFT (Thin Film Transistor) element is loaded, and the decline of the manufacturing yielding percentage owing to the pollution and the electrostatic damage.

25 Consequently, in place of the mechanical rubbing method, there is drawn attention a photo-alignment control technique capable of causing the liquid crystal alignment without touching. See Japanese Patent Application Publication Hei 07-318942 (basic application of USP 5,604,615), etc.

This technique is a technique for realizing

directionality and a pre-tilt angle of the liquid crystal alignment in an organic alignment film formed on a transparent substrate by causing a chemical change of molecules composing the organic alignment film in

- 5 accordance with the polarized direction of an ultraviolet ray irradiating the organic alignment film. Consequently, the technique can prevent occurrence of the pollution owing to the dust risen at the time of the mechanical rubbing and the electrostatic damage to the board on
- 10 which the TFT element is loaded, and can prevent the decline of the manufacturing yielding percentage.

- Furthermore, because the technique can make the polarized ultraviolet ray irradiate only fine areas, the liquid crystal alignment of the fine areas in the liquid
- 15 alignment film can easily be done. Therefore, the improvement in a visual field angle can be made by performing division alignments of one liquid crystal alignment film. To adduce an actual example, for making main viewing angle directions of a liquid crystal display
- 20 element even in the vertical direction and the horizontal direction, the technique executes a liquid crystal alignment treatment of irradiating liquid crystal alignment films of upper and lower boards in four
- 25 respective divided areas "aa", "bb", "cc" and "dd" of one dot 70, shown in Fig. 7, with a polarized ultraviolet ray so that the liquid crystal alignments of the lower substrate become the directions of the dotted line arrow heads and so that the liquid crystal alignments of the upper substrate become the full line arrow heads.
- 30 Because main viewing angle directions of respective divided areas become the directions of the stars in the

figure as the results, the main viewing angle direction of the whole liquid crystal display element becomes a mixture of viewing angle characteristics in four directions of the up, the down, the right and the left.

- 5 Consequently, an inversion phenomenon and the decline of contrast can be suppressed, so that the visual field angle becomes good.

Incidentally, in this case, for using the main viewing angle directions of the liquid crystal display element of two directions of the right and the left, it is applicable to divide one dot into two areas.

However, in a case where the liquid crystal alignments are executed by diving one dot into two or four areas like the prior art technique, because alignment disorder occurs at boundaries of the divided areas (division boundaries), it is necessary to shade the upper substrate where a color filter is formed from rays penetrating the divided areas. For this reason, it is necessary to dispose shading areas at not only between dots but also crossing areas in a dot as denoted by the reference numerals 70a and 70b in Fig. 7. Consequently, a decline of aperture ratio of a dot and a decline of the transmissivities of rays are caused, and thereby there is caused a problem that the display quality of the liquid crystal display element declines as a result. The tendency becomes remarkable as the dot becomes finer, and the manufacturing yielding percentage also becomes declined.

Furthermore, when manufacturing such a liquid crystal display element, the liquid crystal alignment is performed by the irradiation of the polarized ultraviolet

ray in conformity with the technique. But, the technique has problems such that it is difficult for the technique to define the alignment direction of a liquid crystal strictly and also it is difficult for the technique to develop a prescribed pre-tilt angle stably in comparison with the mechanical rubbing method. Consequently, problems of declinations of display quality such as the occurrence of unevenness of alignment and a declination of transmissivity and contrast of a display using a liquid crystal cell the liquid crystal alignment treatment of which has been performed by irradiating a polarized ultraviolet ray thereon are not resolved yet. That has been a great barrier to perform the mass production thereof.

SUMMARY OF THE INVENTION

The present invention aims to resolve the aforesaid problems of the prior art, and aims to provide a liquid crystal display element having a superior viewing angle characteristic without causing a decline of aperture ratio and a decline of transmissivity of a ray at a pixel composed of a group of three dots of an R-dot, a G-dot and a B-dot, or each dot. Moreover, the present invention also aims to realize a good liquid crystal alignment direction and a stable and even pre-tilt angle by means of a polarized ultraviolet ray without a decline of the manufacturing yielding percentage at the time of manufacturing such a liquid crystal display element.

The inventor of the present invention found the following facts and has completed a liquid crystal display element of the present invention. That is, the

main viewing angle direction of the whole liquid crystal display element can be adjusted in an intended direction by performing a division alignment treatment of a liquid crystal alignment film on a transparent substrate while
5 keeping a unique alignment direction at each pixel not dividing a pixel (ordinary composed of a group of an R-dot, a G-dot and a B-dot) and differentiating alignment directions at least between two pixels so as to be able to obtain an intended main viewing angle direction. And
10 further, if a dot is still finer, the superior viewing angle characteristic can be obtained by performing the adjustment of the main viewing angle direction by the dot, not by performing the control of the main viewing angle by the pixel.

15 Furthermore, the inventor of the present invention found the following fact and has completed a method for manufacturing a liquid crystal display element of the present invention. That is, it is possible to develop a superior viewing angle characteristic and an even and
20 stable liquid crystal alignment and pre-tilt angle of the liquid crystal display element without a decline of the manufacturing yielding percentage by irradiating a liquid crystal alignment film on a transparent substrate by the pixel and/or by the dot with divided polarized
25 ultraviolet rays in a manner that the irradiation of the polarized ultraviolet ray is first performed for regulating liquid crystal alignment directions, and that the transparent substrate is next rotated, and further that the divisional irradiation of the polarized
30 ultraviolet ray is again performed by the pixel or by the dot for regulating the pre-tilt angle of the liquid

crystal.

That is to say, according to a first aspect of the present invention, there is provided a liquid crystal display element including a pair of transparent
5 substrates, a liquid crystal sandwiched between the pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of the respective transparent substrates, wherein the liquid crystal alignment films are aligned dividedly by a dot
10 and/or by a pixel, and liquid crystal alignment directions at two dots or more and/or at two pixels or more differ from each other so that it is possible to obtain an intended main viewing angle direction.

It is needless to say that the division by the dot
15 and the division by the pixel may be intermingled by performing a division alignment composed of alignments by the dot in some areas of the liquid crystal display element and alignments by the pixel in the other areas of the liquid crystal display element.

Furthermore, according to a second aspect of the present invention, there is provided a method for manufacturing a liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between the pair of transparent substrates,
25 and liquid crystal alignment films formed on liquid crystal side surfaces of the respective transparent substrates, the method comprising the steps of (a) forming ultraviolet ray responsive type liquid crystal alignment films on the pair of transparent substrates,
30 (b) irradiating the liquid crystal alignment films on the transparent substrates parallel to a reference plane with

a polarized ultraviolet ray dividedly by a dot and/or by a pixel so that liquid crystal alignment directions at two dots or more and/or at two pixels or more differ from each other for obtaining an intended main viewing angle direction so as to regulate an alignment direction of the liquid crystal, and (c) irradiating the transparent substrate, on which the liquid crystal alignment films irradiated with the polarized ultraviolet ray at the step (b) are formed, with the polarized ultraviolet ray dividedly by the pixel for developing a pre-tilt angle after rotating the transparent substrate on the reference plane so that the transparent substrate turns to a direction different from its direction in the step (b).

It is needless to say that the division by the pixel and the division by the dot may be intermingled in a liquid crystal display element also in this case.

According to the aforementioned aspects of the present invention, a liquid crystal display element is manufactured by irradiating divided area thereof by the pixel and/or by the dot with a polarized ultraviolet ray without using the conventional mechanical rubbing method. Consequently, the manufactured liquid crystal display element exhibits a superior viewing angle characteristic without a decline of its aperture ratio, a decline of its transmissivity of rays and a decline of its manufacturing yielding percentage. Moreover, because the division irradiation of the polarized ultraviolet ray is performed at predetermined two steps, good alignment directions and a stable and uniform pre-tilt angle of liquid crystal molecules can be realized. Consequently, an electro-optical characteristic of the manufactured liquid crystal

display element becomes good.

BRIEF DESCRIPTION OF THE DRAWINGS

5 The above and other objects, features and advantages of the present invention will become more apparent from the following description of the presently preferred exemplary embodiments of the invention taken in conjunction with the accompanying drawings, in which:

10 Fig. 1 is a schematic plan view showing an example, in which liquid crystal alignment directions are made to be different among four pixels, of division alignments of a liquid crystal alignment film of a liquid crystal display element according to the present invention;

15 Fig. 2 is a schematic plan view showing an example, in which liquid crystal alignment directions are made to be different among four dots, of division alignments of a liquid crystal alignment film of a liquid crystal display element according to the present invention;

20 Fig. 3 is a block diagram showing a schematic structure of a ultraviolet ray irradiation apparatus to be used in a first embodiment of the present invention;

Fig. 4A and Fig. 4B are explanatory views showing polarized ultraviolet ray irradiation processes of the first embodiment of the present invention;

25 Fig. 5 is a view showing a viewing angle characteristic of a liquid crystal panel of the first embodiment of the present invention;

30 Fig. 6 is a view showing a viewing angle characteristic of a liquid crystal panel of a first comparative example 1 of the present invention; and

Fig. 7 is an explanatory view showing a

conventional division alignment method where liquid crystal alignment directions are made to be different among four areas of one dot.

5 DESCRIPTION OF THE PREFERRED EMBODIMENTS

At first, a description is given to a liquid crystal display element of the present invention.

The liquid crystal display element of the present invention has a structure similar to an ordinary TN
10 (Twisted Nematic) liquid crystal element that basically includes a liquid crystal sandwiched between a pair of transparent substrates, for example substrates made of glass, and liquid crystal alignment films formed on liquid crystal side surfaces of the transparent
15 substrates.

In the present invention, liquid crystal alignment directions of the liquid crystal alignment films are divided by the pixel or by the dot for improving its viewing angle characteristic. However, the division is
20 not made in a pixel, but the liquid crystal alignment directions are made to be different from each other among two or more pixels or dots so that an intended main viewing angle direction can be obtained. For example, in a case where the main viewing angle directions are made
25 to be two directions facing to the left and the right, the liquid crystal alignment directions are made to be different from each other between two pixels or two dots. And, in a case where the main viewing angle directions are made to be four directions facing to the up, the down,
30 the left and the right, it may be applicable that the liquid crystal alignment directions are made to be

different from each other among four pixels or dots. In the case where the liquid crystal display element is used for a display of a personal computer, for example, it is preferable that the liquid crystal alignment directions are made to be different from each other among four pixels or dots.

Incidentally, it is preferable that pixels or dots the liquid crystal alignment directions of which are different from each other are disposed to adjoin to each other so that the viewing angle characteristics of the whole liquid crystal display element become even. However, the liquid crystal alignment directions may be disposed regularly or randomly so that the liquid crystal alignment directions are dispersed evenly in the whole liquid crystal display element.

Next, more concrete descriptions are given to examples of the division alignments of the liquid crystal alignment films of liquid crystal display elements according to the present invention.

Fig. 1 shows an example (delta disposition) where four pixels A-D (each pixel is composed of a group of an R-dot, a G-dot, and a B-dot) disposed in the so-called delta arrangement so as to make main viewing angle directions four directions of the up, the down, the right and the left are made to be divisionally aligned and liquid crystal alignment directions are made to be different from each other among them. That is, in the pixels A-D, when the liquid crystal alignment direction of the lower substrate is adjusted to the direction of the dotted line arrow head and the liquid crystal alignment direction of the upper substrate is adjusted to

the direction of the full line arrow head, the main viewing angle direction to each of the pixels becomes the direction of each star. That is, the main viewing angle direction to the pixel A becomes upward; the main viewing angle direction to the pixel B becomes leftward; the main viewing angle direction to the pixel C becomes rightward; the main viewing angle direction to the pixel D becomes downward. Incidentally, main viewing angle directions of pixels hatched likewise in the figure are adjusted to be the same. Consequently, the viewing angle characteristics of a liquid crystal display element having the division liquid crystal alignment films shown in Fig. 1 from vertical directions and horizontal directions becomes improved.

Fig. 2 shows another example (delta disposition) where liquid crystal alignment directions are made to be adjusted not by the pixel but by the dot. Likewise in the case of Fig. 1, to make main viewing angle directions four directions of the up, the down, the right and the left, four dots a-d disposed in the so-called delta arrangement are made to be divisionally aligned, and the liquid crystal alignment directions are made to be different from each other among them. That is, in the dots a-d, when the liquid crystal alignment direction of the lower substrate is adjusted to the direction of the dotted line arrow head and the liquid crystal alignment direction of the upper substrate is adjusted to the direction of the full line arrow head, the main viewing angle direction to each of the dots becomes the direction of each star. That is, the main viewing angle direction to the dot a becomes leftward; the main viewing angle

direction to the dot b becomes rightward; the main viewing angle direction to the dot c becomes upward; the main viewing angle direction to the dot d becomes downward. Incidentally, main viewing angle directions of dots hatched likewise in the figure are adjusted to be the same. Consequently, the viewing angle characteristics of a liquid crystal display element having the division liquid crystal alignment films shown in Fig. 2 from vertical directions and horizontal directions also becomes improved.

Next, a description is given to a method for manufacturing a liquid crystal display element of the present invention.

A characteristic feature of the method for manufacturing a liquid crystal display element is to include a liquid crystal alignment treatment process composed of the following processes (a) - (c):

PROCESS (a)

First, an ultraviolet light responsive type liquid crystal alignment film is formed on both of a pair of transparent substrates, respectively.

A substrate used for a TN liquid crystal cell conventionally can be used as one of the pair of the transparent substrates. There can be enumerated, for example, a transparent glass substrate the pixel density of which is 114 thousand pixels per cm^2 and on which a high temperature polysilicon type TFT element having a diagonal length of 0.55 inches (1.397 cm) or more and having the number of pixels of 113 thousands or more dots is formed, and a transparent glass substrate the pixel

density of which is 10 thousand pixels per cm^2 and on which a high temperature polysilicon type TFT element having a diagonal length of 2.5 inches (6.25 cm) or more and having the number of pixels of 180 thousands or more dots is formed. That is, the present invention is useful particularly in a liquid crystal display element having a high pixel density. In a case of a transparent glass substrate having a high temperature polysilicon type TFT formed by applying a semiconductor process at about 1,000°C, the present invention is especially preferable in a case of a pixel density of 100 thousand pixels per cm^2 or more. And, in a case of a transparent glass substrate having a low temperature polysilicon type TFT formed by using a re-crystallization process with a laser, the present invention is especially preferable in a case of a pixel density of 10 thousand pixels per cm^2 or more.

As materials of the ultraviolet light responsive type liquid crystal alignment film, materials having characteristics of developing the alignment of a liquid crystal in a direction perpendicular to the polarized direction of a polarized ultraviolet ray may be used. For example, a poly amicacid macromolecular material being a polyimide type photo-alignment material shown in USP 5,731,405 may be used.

The thickness of the liquid crystal alignment film is ordinary 0.02-0.08 μm .

An offset printing method, a spin coating method or the like can appropriately be selected in accordance with the material of the liquid crystal alignment film to be used as a method for forming the liquid crystal alignment film.

Furthermore, a glass substrate, on a surface of which a transparent conducting film (such as ITO (Indium Tin Oxide)) is formed, or the like can be used as the other of the pair of the transparent substrates.

5

PROCESS (b)

Next, a liquid crystal alignment film on a transparent substrate parallel to a reference plane is irradiated by a polarized ultraviolet ray (a first irradiation) dividedly by the pixel and/or by the dot in a manner that liquid crystal alignment directions differ from each other among two or more pixels and/or dots so that an intended main viewing angle direction can be obtained for regulating the alignment direction of the liquid crystal. For set the transparent substrate parallel to the reference plane in this case, the transparent substrate may be placed on, for example, a steel flatbed (reference plane).

An ultraviolet ray that has passed through a polarization filter is used as the polarized ultraviolet ray. An ordinary polarization filter that makes only a ray having a predetermined direction pass is used as the polarization filter.

It is preferable to use an electrodeless UV lamp that has a high output level, a long life span and further high uniformity, i.e. little dispersion of illuminance, as the light source of the polarized ultraviolet ray.

Moreover, it is preferable that a polarized ultraviolet ray irradiation angle, namely an elevation angle to the reference plane in the first irradiation is

within a range of 50 degrees to 90 degrees not for declining the contrast. 90 degrees is especially preferable.

Moreover, as a technique of the irradiation of the polarized ultraviolet ray in the manner of the division by the pixel or by the dot, it is useful to use a shading mask for preventing the irradiation of the polarized ultraviolet ray to areas other than the pixels of the dots to which the polarized ultraviolet ray should be irradiated, or to scan the polarized ultraviolet ray so as to irradiate only the intended pixels or dots.

Incidentally, the R-dots, the G-dots and the B-dots may be arranged in conformity with the delta arrangement or a stripe arrangement.

PROCESS (c)

Next, the transparent substrate, on which the liquid crystal alignment film irradiated by the polarized ultraviolet ray at the first irradiation in the process (b), is rotated on the reference plane. In this case, the transparent substrate is rotated to a direction different from the direction in the process (b). And then, the polarized ultraviolet ray in a state of being divided by the pixel or by the dot is again irradiated (a second irradiation) to the liquid crystal alignment film on the rotated transparent substrate for developing the pre-tilt angle.

The reason why the transparent substrate is rotated is that a stable pre-tilt angle cannot be induced if the transparent substrate is not rotated. Now, the rotation angle is preferably within a range of 45-90 degrees, more

preferably 90 degrees.

Moreover, the irradiation angle of the polarized ultraviolet ray at the second irradiation, namely an elevation angle to the reference surface, is preferably
5 within a range of 50-80 degrees. If the angle is out of the range, the pre-tilt angle becomes small and the angle tends to become unstable.

Incidentally, the ratio between the ultraviolet ray irradiation energy at the first irradiation in the
10 process (b) and the ultraviolet ray irradiation energy at the second irradiation in the process (c) is preferably 100 : 1 to 1 : 1, more preferably 5 : 1 to 3 : 1. When the ultraviolet ray irradiation energy at the second irradiation becomes relatively larger than the range, the
15 pre-tilt angle tend to be declined. In addition, the similar liquid crystal alignment treatment is performed to the other transparent substrate.

By composing a liquid crystal cell in conformity
20 with the conventional method with the transparent substrates the liquid crystal alignment treatment of which has been performed in conformity with the aforesaid processes (a)-(c), and by assembling a liquid crystal driving device and the like similarly to the
25 manufacturing method for the conventional TN liquid crystal display element, a liquid crystal display element of the present invention can be obtained. Because the thus obtained liquid crystal display element realizes a stable and constant division alignment of its liquid
30 crystal and has a stable pre-tilt angle, the viewing angle characteristic thereof is improved, and the liquid

crystal display element can be manufactured at a high manufacturing yielding percentage, and further has a good electro-optical characteristic.

5 [EMBODIMENT]

Hereafter, the present invention is concretely described in regard to embodiments.

EMBODIMENT 1

10 A polyimide type liquid crystal alignment agent (see USP 5,731,405) was coated in conformity with a conventional method on a glass substrate on which a low temperature polysilicon type TFT element having a diagonal length of 3.5 inches and the number of display
15 dots of 200 thousands or more had been formed in conformity with a conventional method, and was coated on another glass substrate equipped with a color filter and an ITO transparent electrode on which any pattern is not formed as an opposed substrate to the aforesaid glass
20 substrate. And then, the polyimide type liquid crystal alignment agent was provisionally dried for 30 minutes at 80°C. And further, the polyimide type liquid crystal alignment agent was mainly dried for 60 minutes at 190°C for forming a liquid crystal alignment film.

25 Next, a liquid crystal alignment treatment was performed to adjoining four pixels so as to obtain the main viewing angle directions shown in Fig. 1 by using an ultraviolet ray irradiation apparatus (or an electrodeless lamp, "H" bulb manufactured by Fusion UV
30 Systems, Inc.) as shown in Fig. 3 and a shading mask for irradiating only predetermined pixels on the glass

substrate with the polarized ultraviolet ray. That is, a
ultraviolet ray $h\nu$ from a lamp unit 3 equipped with a
light bulb 2 was made to pass a polarization unit 4, the
polarization degree of which was about 10 : 1, and a
5 filter 5 cutting waves having wavelengths of 3,000 nm or
less. And then, a P polarized ultraviolet ray
(polarization axis is 5) $Ph\nu$, which was the
aforementioned ultraviolet ray $h\nu$ after passing the
polarization unit 4 and the filter 5, was irradiated at
10 two steps by the pixel on the liquid crystal alignment
film side surface of the transparent board 1 on which the
liquid crystal alignment film had been formed as shown in
Fig. 4A and Fig. 4B. Incidentally, the accumulated
amount of the polarized ultraviolet ray of each pixel was
15 30 J/cm².

(CONDITIONS OF FIRST IRRADIATION)

elevation angle (irradiation angle): 80°

irradiation energy: 25 J/cm²

20 ultraviolet ray intensity: 100 ± 10 mW/cm²

(CONDITIONS OF SECOND IRRADIATION)

transparent substrate rotation angle: 90°

elevation angle (irradiation angle): 80°

25 irradiation energy: 5 J/cm²

ultraviolet ray intensity: 100 ± 10 mW/cm²

The similar liquid crystal alignment treatment was
performed to the transparent substrate on the other side.

30

A pair of the transparent substrates to which the

aforementioned liquid crystal alignment treatment was respectively performed by irradiating the polarized ultraviolet ray were affixed to each other with a gap of 3.5 μm so as to take the liquid crystal alignment directions shown in Fig. 1. A TN liquid crystal cell was made by inserting a liquid crystal into the gap. The disposition of the polarizing plate was made to be a normal white disposition where the polarization axis is perpendicular to the alignment axis.

10 A TN liquid crystal panel was made in conformity with a conventional method by using the TN liquid crystal cell. When the viewing angle characteristics of the obtained TN liquid crystal panel were measured, the viewing angle characteristics were $\pm 75^\circ$ in the up, the down, the right and the left directions. And the contrast of 150 or more was obtained (see Fig. 5).

15 Incidentally, since the two-step irradiations of the polarized ultraviolet ray were performed to the liquid crystal panel of the embodiment for the liquid crystal alignment treatment, the pre-tilt angle was 5.7° , and it was stable and constant.

EMBODIMENT 2

25 A TN liquid crystal panel was made similarly to the embodiment 1 except that the liquid crystal alignment treatment similar to that of the embodiment 1 was performed to four adjoining dots shown in Fig. 2 in place of four adjoining pixels. When viewing angle characteristics of the obtained TN liquid crystal panel were measured, viewing angle characteristics and contrasts substantially the same as those of the TN

liquid crystal panel of the embodiment 1 were obtained.

Incidentally, since the two-step irradiations of the polarized ultraviolet ray were performed to the TN liquid crystal panel of the embodiment for the liquid crystal alignment treatment, the pre-tilt angle was 5.8°, and it was stable and constant.

COMPARATIVE EXAMPLE 1

A TN liquid crystal panel was made similarly to the embodiment 1 except that the liquid crystal alignment treatment similar to that of the embodiment 1 was performed to one dot divided into four areas in place of four adjoining dots. When viewing angle characteristics of the obtained TN liquid crystal panel were measured, viewing angle characteristics substantially the same as those of the TN liquid crystal panel of the embodiment 1 were obtained. However, contrasts were declined greatly to below 30 (see Fig. 6).

However, since the two-step irradiations of the polarized ultraviolet ray were performed to the TN liquid crystal panel of the comparative example for the liquid crystal alignment treatment, the pre-tilt angle was 5.2°, and it was stable and constant.

Although the invention has been described in its preferred form with a certain degree of particularity, obviously many changes and variations are possible therein. It is therefore to be understood that the present invention may be practiced than as specifically described herein without departing from scope and the spirit thereof.

WHAT IS CLAIMED IS:

1. A liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said respective transparent substrates, wherein:

said liquid crystal alignment films are aligned dividedly by a dot and/or by a pixel, and liquid crystal alignment directions at two dots or more and/or at two pixels or more differ from each other so that it is possible to obtain a predetermined main viewing angle direction.

2. A liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said respective transparent substrates, wherein:

said liquid crystal alignment films are aligned dividedly by a dot, and liquid crystal alignment directions at two dots or more differ from each other so that it is possible to obtain a predetermined main viewing angle direction.

3. The liquid crystal display element according to claim 2, wherein said liquid crystal alignment directions at four dots differ from each other.

4. The liquid crystal display element according to

claim 2, wherein said liquid crystal alignment directions at dots adjoining to each other differ from each other.

5 5. A liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said respective transparent substrates, wherein:

10 said liquid crystal alignment films are aligned dividedly by a pixel, and liquid crystal alignment directions at two pixels or more differ from each other so that it is possible to obtain a predetermined main viewing angle direction.

15 6. The liquid crystal display element according to claim 5, wherein said liquid crystal alignment directions at four pixels differ from each other.

20 7. The liquid crystal display element according to claim 5, wherein said liquid crystal alignment directions at pixels adjoining to each other differ from each other.

25 8. A method for manufacturing a liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said respective transparent substrates, said method comprising the steps of:

30 forming ultraviolet light responsive type liquid

crystal alignment films on said pair of transparent substrates;

5 irradiating said liquid crystal alignment films on said transparent substrates parallel to a reference plane with a polarized ultraviolet ray dividedly by a dot so that liquid crystal alignment directions at two dots or more differ from each other for obtaining a predetermined main viewing angle direction so as to regulate an alignment direction of said liquid crystal; and

10 irradiating said transparent substrate, on which said liquid crystal alignment films irradiated with said polarized ultraviolet ray are formed, with said polarized ultraviolet ray dividedly by the dot for developing a pre-tilt angle after rotating said transparent substrate
15 on said reference plane so that said transparent substrate turns to a direction different from its direction at the time of said irradiating said liquid crystal alignment films.

20 9. The method for manufacturing a liquid crystal display element according to claim 8, wherein said liquid crystal alignment directions at four dots differ from each other.

25 10. The method for manufacturing a liquid crystal display element according to claim 8, wherein said liquid crystal alignment directions at dots adjoining to each other differ from each other.

30 11. A method for manufacturing a liquid crystal display element including a pair of transparent

substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said respective transparent substrates, said method comprising the steps of:

forming ultraviolet light responsive type liquid crystal alignment films on said pair of transparent substrates;

irradiating said liquid crystal alignment films on said transparent substrates parallel to a reference plane with a polarized ultraviolet ray dividedly by a pixel so that liquid crystal alignment directions at two pixels or more differ from each other for obtaining a predetermined main viewing angle direction so as to regulate an alignment direction of said liquid crystal; and

irradiating said transparent substrate, on which said liquid crystal alignment films irradiated with said polarized ultraviolet ray are formed, with said polarized ultraviolet ray dividedly by the pixel for developing a pre-tilt angle after rotating said transparent substrate on said reference plane so that said transparent substrate turns to a direction different from its direction at the time of said irradiating said liquid crystal alignment films.

12. The method for manufacturing a liquid crystal display element according to claim 11, wherein said liquid crystal alignment directions at four pixels differ from each other.

13. The method for manufacturing a liquid crystal

display element according to claim 11, wherein said liquid crystal alignment directions at pixels adjoining to each other differ from each other.

5 14. A method for manufacturing a liquid crystal display element including a pair of transparent substrates, a liquid crystal sandwiched between said pair of transparent substrates, and liquid crystal alignment films formed on liquid crystal side surfaces of said
10 respective transparent substrates, said method comprising the steps of:

 forming ultraviolet light responsive type liquid crystal alignment films on said pair of transparent substrates;

15 irradiating said liquid crystal alignment films on said transparent substrates parallel to a reference plane with a polarized ultraviolet ray dividedly by a dot and/or by a pixel so that liquid crystal alignment directions at two dots or more and/or at two pixels or
20 more differ from each other for obtaining a predetermined main viewing angle direction so as to regulate an alignment direction of said liquid crystal; and


 irradiating said transparent substrate, on which said liquid crystal alignment films irradiated with said
25 polarized ultraviolet ray are formed, with said polarized ultraviolet ray dividedly by the pixel for developing a pre-tilt angle after rotating said transparent substrate so that said transparent substrate turns to a direction different from its direction at the time of said
30 irradiating said liquid crystal alignment films.

ABSTRACT

An ultraviolet light responsive type liquid crystal alignment films are formed on opposing surfaces of a pair of transparent substrates constituting a liquid crystal cell. Next, the liquid crystal alignment films on the transparent substrates parallel to a reference plane are irradiated by a polarized ultraviolet ray dividedly by the pixel or by the dot so as to regulate an alignment direction of the liquid crystal. Furthermore, the transparent substrate that has been irradiated by the polarized ultraviolet at the previous step is irradiated by the polarized ultraviolet ray dividedly by the pixel or by the dot for developing a pre-tilt angle after rotating the transparent substrate on the reference plane so that the transparent substrate turns to a direction different from its direction at the previous step.

[illegible]

FIG. 2



2023-03-23 10:00

FIG. 3




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6





FIG. 7



DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

LIQUID CRYSTAL DISPLAY ELEMENT AND METHOD FOR MANUFACTURING IT

Case No, 09792909-4653, the specification of which

(check one) X is attached hereto
 was filed on _____, as
 Application Serial No. _____
 and was amended on _____
 (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent Office all information which is known to me to be material to the patentability of this application in accordance with Titel 37, Code of Federal Regulations. 1.56¹

I do not know and do not believe this invention was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, and I believe that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as identified below:

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below:

Prior Foreign Application(s)

Number

P11-294626

Country

Japan

Date

October - 15, 1999

and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the above listed application on which priority is claimed:

¹ (b) Under this section, information is material to patentability when it is not cumulative to information already of record or being made of record in the application, and

(1) It establishes, by itself or in combination with other information, a *prima facie* case of unpatentability of a claim; or

(2) It refutes, or is inconsistent with, a position the application takes in:

(i) opposing an argument of unpatentability relied on by the Office, or

(ii) asserting an argument of patentability.

A *prima facie* case of unpatentability is established when the information compels a conclusion that a claim is unpatentable under the preponderance of evidence, burden of proof standard, giving each term in the claim its broadest reasonable construction consistent with the specification, and before any consideration is given to evidence which may be submitted in an attempt to establish a contrary conclusion of patentability.

00012184500

Prior Foreign Application(s)
Number

Country

Date

If no priority is claimed, I have identified all foreign patent applications filed prior to this application:

Prior Foreign Application(s)
Number

Country

Date

And I hereby appoint Joseph A. Mahoney (Reg. No. 38,956), Howard B. Rockman (Reg. No. 22,190), Jordan A. Sigale, (Reg. No. 39,028), Michael A. Molano (Reg. No. 39,777), Michael L. Kiklis (Reg. No. 38,939), Janelle D. Strode (Reg. No. 34,738), Kevin W. Guynn (Reg. No. 29,972), David R. Metzger (Reg. No. 32,919), Jennifer Hammond (Reg. No. 41,814), Lana Knedlik (Reg. No. 42,748), John F. Griffith (Reg. No. 44,137), Marina Saito (Reg. No. 42,121), Alison P. Schwartz (Reg. No. 43,863), Christopher P. Rauch (Reg. No. 45,034), Francisco Rubio-Campos (Reg. No. 45,358), Brian J. Gill (Reg. No. 46,727) and Shashank S. Upadbye, all members of the firm of Sonnenschein, Nath & Rosenthal

Telephone 312/876-0200 Ext. 2578

my attorneys with full power of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith and direct that all correspondence be forwarded to:

SONNENSCHN NATH & ROSENTHAL
80th Floor - Sears Tower
233 S. Wacker Drive, Chicago, IL 60606

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor YOSHIMASA SAITO

Inventor's signature Yoshimasa Saito Date September 12, 2000
Residence KANAGAWA, JAPAN
Citizenship JAPANESE
Post Office Address c/o SONY CORPORATION 7-35, KITASHINAGAWA
6-CHOME, SHINAGAWA-KU, TOKYO, JAPAN

Full name of second inventor _____

Inventor's signature _____ Date _____
Residence _____
Citizenship _____
Post Office Address _____

Full name of third inventor _____

Inventor's signature _____ Date _____
Residence _____
Citizenship _____
Post Office Address _____